Inferring complex textile shape from an integrated carbon black-infused ecoflex-based bend and stretch sensor array

Leonardo A. García-García
l.a.garcia-garcia@sussex.ac.uk
University of Sussex
Brighton, United Kingdom

George Valsamakis
G.Valsamakis@sussex.ac.uk
University of Sussex
Brighton, United Kingdom

Paul M. Kreitmair
pk318@sussex.ac.uk
University of Sussex
Brighton, United Kingdom

Niko Munzenrieder
Niko.Munzenrieder@unibz.it
Free University of Bozen-Bolzano
Bolzano, Italy
University of Sussex
Brighton, United Kingdom

Daniel Roggen
daniel.roggen@ieee.org
University of Sussex
Brighton, United Kingdom

ABSTRACT

We demonstrate how an array of custom-made strain and bend sensors could be integrated into a stretchable sleeve to infer the textile deformation. The angles and elongation measured by the sensors can be used by an optimisation-based algorithm to infer the textile geometrical model by minimising a loss function. We evaluated this on 4 shapes highlighting different body-part characteristics. We demonstrated that a 3.11 mm reconstruction error on complex geometries can be reduced up to 0.08 mm with the computation of angles. This proves the potential of the proposed prototype for capturing the shape of a body parts, muscle density measurement, body shape acquisition, the fabrication of orthoses and prostheses, or to perform movement sensing for human activity recognition, where it could be included in sports leggings for biomechanical analysis, or in everyday garments for motion and gesture sensing.

KEYWORDS

Smart textile, wearable sensing, textile sensing, activity recognition

ACM Reference Format:

Leonardo A. García-García, George Valsamakis, Paul M. Kreitmair, Niko Munzenrieder, and Daniel Roggen. 2021. Inferring complex textile shape from an integrated carbon black-infused ecoflex-based bend and stretch sensor array. In *Proceedings of (HASCA' 21)*. ACM, New York, NY, USA, 7 pages. <https://doi.org/10.1145/1122445.1122456>

1 INTRODUCTION

Human body shape digitisation for 3D modelling has been explored in a wide range of sectors. Typical applications are body posture tracking [1, 11–13, 18], rehabilitation [14], muscle volumetric measurements [21], fabrication of orthoses and prostheses [4], creation of realistic models to fit clothing [2, 20], and for virtual reality and animation [9]. Generally, these applications rely on complex and expensive techniques such as Magnetic Resonance Imaging (MRI) or Computerised Tomography (CT) scans [6, 7].

Wearable devices with accelerometers and magnetic field sensors have been utilised for textile shape sensing [10], however, the accuracy is still affected by gaps between sensors, calibration, dynamic acceleration and magnetic disturbances, or they require reliable wireless connection and complex machine learning algorithms [1, 12]. More fundamentally, despite advances in electronics miniaturisation, deploying an array of such sensors in a textile is costly, especially compared to much simpler passive sensors such as simple elongation and bend sensors which are essentially resistors whose value is modified by the component geometry. These can be resistive [17, 19] or capacitive [3] made of elastomers and carbonaceous fillers. Although the latter showed lower hysteresis, resistive sensors have a higher gauge factor (GF), being highly sensitive to small changes in strain.

Permission to make digital or hard copies of all or part of this work for personal or classroom use is granted without fee provided that copies are not made or distributed for profit or commercial advantage and that copies bear this notice and the full citation on the first page. Copyrights for components of this work owned by others than ACM must be honored. Abstracting with credit is permitted. To copy otherwise, to republish, to post on servers or to redistribute to lists, requires prior specific permission and/or a fee. Request permissions from permissions@acm.org.

HASCA' 21, 2021, Global

© 2021 Association for Computing Machinery.

ACM ISBN 978-1-4503-XXXX-X/18/06...\$15.00

<https://doi.org/10.1145/1122445.1122456>

New technologies such as the use of badge-reel stretch sensors have been using also for posture monitoring [11], however, they still lacking the conformability to the human body shape offered by functional flexible and stretchable sensors [8, 15, 18]. This property has been explored for the fabrication of systems formed by arrays of sensors for shape sensing [16] and for the measurement of 3D surface deformations [8].

The contributions of this paper are as follows:

- A stretchable and conformable textile sleeve integrated with a grid of specially synthesised and tailored strain and bend sensors to increase definition on the reconstruction.
- A custom production process for the passive strain and bend sensors based on ecoflex infused with carbon-black, which aims to eventually reduce costs compared to using active sensors (e.g. MEMS-based IMUs) and could be included within an industrial production process.
- An optimisation-based shape reconstruction algorithm which enables the reconstruction of 3D geometries based on the elongation and bend data reported by the sensor. The algorithm optimises the coordinates of the vertices of a mesh until a minimum error is obtained between the sensor-reported elongations and angles, and the reconstructed mesh elongations and angles.
- Compared to the closest reported previous work [16] which employed commercial sensors which only measured elongation, the novelty of this work is to include both elongation and bend sensors. While only shapes with circular symmetry could be sensed in [16], our work can be applied to shapes with different radii on the cross section and with bending features perpendicular to the cross section. This allows to capture more complex geometries including elbows or bumps, which could be useful in body-shape sensing applications, such as orthotics.
- Finally, we discuss how this textile shape sensing can be used in the context of human activity recognition when included in sports garments or everyday clothing, thereby allowing unobtrusive motion sensing. This complements current sensing approaches based on wearable devices.

2 APPROACH

A shape inference algorithm is used jointly with an array of flexible sensors in a stretchable textile sleeve. Figure 1a) shows the configuration of the textile sleeve. This is formed by 4 rings of stretchable(SS) to measure the rates of changes in length and bending sensors(BS) alternated to quantify the changes in direction on the cross section. These rings are connected each other by a row of 10 bending sensors(B),

which will measure changes in direction perpendicular to the cross section. The 3D shape inference is carried out using an optimisation process based on the difference between the data obtained from the sensors when at rest and when they are in an active state (stretch or bend). The algorithm was developed and tested in Matlab using a digital simulation of arbitrary topologies, matching the hardware system and assessing configurations with higher number of sensors. To achieve this, two geometries are generated, a *target* geometry and an *inference* geometry. The former has a fixed topology which is the digital representation of the array of sensors, given the reading of the sleeve's sensors after conforming onto a physical body. The topology of the latter starts as a cylinder, and will iterate to match the *target* geometry. Each geometry is formed by a set of n nodes ($P_i(x_i, y_i, z_i) \in \mathbb{R}^3$) connected to m neighbour nodes through edges defined using a $n \times m$ connectivity matrix. Sensors' connections are denoted by the nodes and the lengths by the edges. Three parameters are defined in the simulation, the edges' lengths (e_{target}), obtained from the sensors' strain ϵ , and two different sets of angles, the angles between segments on the geometry's cross section, ($\theta_{C_{tar}}$), and the angles between segments connecting each cross section along the geometries' length, ($\theta_{L_{tar}}$), measured with bend sensors.

The inference geometry's nodes initial condition is a cylindrical array with diameter and length larger than the target shape, and the inference to the target shape is undertaken with an optimisation process that seeks to optimise the nodes' coordinates, (x_i, y_i, z_i), so that the edges' lengths (e_{inf}) and the angles (θ_{inf}) of the *inferred shape* matches those measured by the sensors. This is achieved using a loss function L . This function determines the difference between the inferred shape and the sensors' readings and is the sum of the squared differences between lengths and angles of the *inferred* shape and those of the *target* shape, as shown in equation 1:

$$L = \sum_{i=1}^E \left(\left((e_{inf,i} - e_{tar,i})^2 \cdot \lambda_1 \right) + (1 - \lambda_1) \cdot \left(\left(\theta_{C_{inf,i}} - \theta_{C_{tar,i}} \right)^2 \cdot \lambda_2 \right) + \left(\left(\theta_{L_{tar,i}} - \theta_{L_{inf,i}} \right)^2 \cdot (1 - \lambda_2) \right) \right) \quad (1)$$

Both geometries must have the same number of nodes, edges, and the same number of neighbours or connectivity. Moreover, two weighting factors were added, $0 < \lambda_1 < 1$ and $0 < \lambda_2 < 1$. λ_1 assigns a higher importance to the matching lengths between the inferred shape and the sensor readings and a lower importance ($1 - \lambda_1$) to the matching angles on the cross section; λ_2 assigns a higher importance to the angles on the cross section and the remaining value ($1 - \lambda_2$) to the angles perpendicular to the cross section. The loss

Figure 1: Sensors array and simulation topology. a) The array of sensors, formed by four rings made of Strain Sensors (SS in turquoise) and Bending Sensors (BS in red) connected in series. These rings are connected through 10 Bending sensors (B in green) that measure changes perpendicular to the cross section. b) Simulation mesh topology, e_i = edges length, θ_{C_i} = angles on the cross section, θ_{L_i} = angles perpendicular to the cross section.

function L is minimised using a Gradient descent algorithm (BFGS Quasi-newton) to compute the partial derivative of the nodes' displacement $\left(\|x_{i_{inf}} - x_{i_{tar}}\|\right)$, with $x_i = (x_i, y_i, z_i)$; then the gradient descent adjust the coordinates to match the distances to those of the sensor readings.

To assess the performance of the algorithm for complex shapes, a virtual representation of the sleeve was developed. Virtual topologies with different curvature features were used to simulate how the real-world sleeve conforms. As the shape geometries have known coordinates, the virtual sleeve is conformed over the shape using the nearest neighbour approximation while retaining the constraints of the real sleeve. The formed sleeve is then processed by the optimisation algorithm and compared.

3 SENSOR-ENHANCED TEXTILE

The system is formed by a textile sleeve with 70 sensors. A textile sleeve was enhanced with an array of bending and stretchable sensors that were designed and fabricated with carbon black conductive nano particles and ecoflex silicone. The array was designed so that it is formed by four long stripes of 5 stretchable sensors alternated with 5 bending sensors, all connected in series, therefore, the end of one

sensor is connected to the end of the following sensor (1a). The "rings" measure shapes' cross section perimeter, they are connected by 3 rows of bending sensors that measure any changes perpendicular to the cross section. The thickness of the sensors is 1.5 mm and their width is 5 mm. Bending sensors are 16 mm while strain sensors are 13 mm.

The material of the sensors was synthesised following the steps depicted in Fig.2, using heptane, Ecoflex (00-30 Smooth-on, Pennsylvania, United States) and carbon black (Vulcan P, Cabot, Boston, Massachusetts, United States) in a ratio of 10:10:1.5. Heptane was used as a non-polar solvent to mix the carbon black in Ecoflex. A mould was designed and 3D printed to shape the sensors by pouring the material in it. For the bending sensors, an additional fibre, sisal, was placed in the bottom of the mould and covered with the piezoresistive material, so that the change in resistance was only influenced by bending rather than the stretching; while no further modification was done for the strain sensors. The sensors were interfaced with filament copper wires as this method showed high reliability during cyclic tests for loading and stretching [5].

Once the solution was cured, the array was removed from the mould and adhered to a textile sleeve using silicone. The smart textile shown in Figure 2 has a inner diameter of 60 mm and it was connected to an interface hardware. The PCB is depicted in Figure 3 and has 6 circuits connected to a microcontroller development system (Teensy 3.2). The data from the 40 sensors on the rings is acquire by four circuits, each one with two 16 channel analogue multiplexers, two operational amplifier, and a digital potentiometers. The resistance values of the 30 bend sensors that connect the rings are read by two circuits built with two 16 channels analogue multiplexers, one digital potentiometer, and one Op Amp. In both cases, the multiplexers connect one sensor at the time with the digital potentiometer to form a voltage divider. The value of the digital potentiometers is adjusted changes with the sensor resistance values to obtain more accurate values. The microcontroller is interfaced over a USB serial line and Matlab is used for data acquisition, storage, and processing.

The sleeve was worn on four shapes with different features. The shapes were specially designed to test the feasibility of the sensors to measure changes in cross section and perpendicular to the cross section. The shapes were designed in Solidworks and exported in STL fie for both, simulation and for 3D printing to perform measurements. The geometries are shown in Fig. 5. A cylinder with a double ellipsis was designed to test different radius over the cross section. Similarly, a cone, a double ellipsis bent cylinder, and a cone with a bump were designed to measure changes in and perpendicular to cross sections with different diameters.

Figure 2: Fabrication process for the sensors. Carbon black and Heptane are put together and mixed. Ecoflex B is added half an hour later and stirred for 5 hours. Ecoflex A is added and stirred for a quarter of an hour. The solution is degassed and poured into a mould. After 24 hours, the array is detached and attached to a elastic textile sleeve.

Smart Textile Calibration

The sleeve was calibrated before performing shape acquisition. A set of 3D printed cylinders with three different diameters, 62, 64 and 70 mm, were used for the calibration. First, the resistance of each sensor was measured at rest (R_0) during 30 min, then the sleeve was placed on a cylinder for 30 min, and removed afterwards. The resistance values were obtained after 10 min of placing or removing the sleeve and averaged to calculate the change in resistance ($\Delta R/R_0$). This process was carried out 5 times for each cylinder, measuring each one of the strain sensors when on the 3D printed parts to compute the change in length ϵ . This was required as each sensor has a different R_0 and degree of strain. The circumference of the rings were calculated with the sum of the thickness of the sleeve and the diameter of the cylinders for each calibration shape. The elongation and the average resistance for each diameter were used in a third degree polynomial obtained with polyfit function in MatLab.

4 EXPERIMENTS AND RESULTS

The implementation of angles for shape inference in the simulation was tested with the STL geometries shown in Fig. 5, and the functionality of the smart textile was tested on 3D printed parts of the same topology. The sensors at rest had a cylindrical shape with a 30 mm radius. The average resistance of the sensors was 321 ± 169 k Ω . The seventh column in Fig. 5 shows the sensors' relative change in resistance ($\Delta R/R_0$) for each measurement.

The algorithm was initially tested on generated cylindrical and elliptical geometries to identify the right set up for number of segments (rings) along the length of the shape and on the cross section (nodes per ring), as well as the appropriate weighting factors λ_1 and λ_2 .

The topology of the simulated sleeve is initially cylindrical. Parametric analysis was done by changing lengths, number

of rings and sensor segments. The mean difference between the inferred vs. target geometries was obtained for different values of λ 's as a measure of accuracy. For each iteration of the minimisation algorithm, the energy used for the optimisation is the output of the function in equation 1. As the algorithm proceeds to find the minimum difference, the energy value minimises until an acceptable tolerance is met. On circular cross section shapes, the lowest energy value of (9.409×10^{-13}) was observed for 20 segments using $\lambda_1 = 0.9$ and $\lambda_2 = 1.0$. While for elliptical cross section it was observed to be 1.697×10^{-12} for 10 segments with $\lambda_1 = 0.3$. For the elliptical cross section with 20 segments, the lowest energy value observed was 1.991×10^{-12} for $\lambda_1 = 1$. This verified the expectation that less weighting in angles prevents the algorithm from inferring to a satisfactory match.

Further tests were conducted using the geometries in Fig. 5. The selected shapes featured characteristics for testing various ranges of λ_1 and λ_2 for discovering combinations that resulted in minimum error. For these shapes, 4 and 8 rings with 11 ring segments were primarily used to match the real sleeve. The simulated sleeve's topology is matched with the STL test geometries by changing the nodes' coordinates using a nearest neighbour approximation, then it becomes the target shape for the optimisation, blue mesh in Fig. 5 column 3. During this process, the constraints of the real sleeve, such as the static lengths of the bend sensors and skew between the rings were retained.

Figure 4 displays the surface plot of the error (axis Z) analysis obtained at various values of λ_1 and λ_2 on axis X and Y, for the 4 shapes individually. The values were obtained from the simulation of the sleeve with 4 rings and 11 nodes per ring. The error was calculated as the mean of coordinate difference between the target and the inferred shapes. The areas in green colour illustrate where λ_1 and λ_2 pairs produced optimum results. These values were later used to test the data from the sleeve sensors, where the target shape is unknown to the algorithm. The algorithm resulted in a best case scenario of 0.11 mm error between target and inferred, compared to 0.89 mm without λ 's. For the majority of the results, there were no significant differences for both λ 's between 0.2 and 0.8 weighting. Shape a) is straight along the length, so inference was accurate for most values of λ_2 , while inference of Shape c) benefited from higher values of λ_2 .

5 DISCUSSION

The system developed enhances shape sensing and reconstruction of 3D shapes by increasing the constraints, by the introducing the computation of angles. For regular shapes where the angles between the edges on the cross section are equal, e. g. circle, the shape reconstruction can be achieved

Figure 3: Readout circuit. A PCB with 6 circuits. 4 used to read the data from 40 stretch and bend sensors on the rings each one with two 16 channels analogue multiplexers, 1 digital potentiometer, and 2 Op Amps. The other 2 circuits read data from 30 bend sensors connecting the rings, each one with a 16 channel analogue multiplexer, 1 digital potentiometer, and 2 Op Amps.

Figure 4: Error analysis of weighting factors (λ_1 and λ_2) on a simulate sleeve with 4 rings and 11 nodes per ring. a) Double oval cylinder, b) two cross sections cone, c) double oval cylinder bent, d) two cross sections cone with a lump.

only by computing the edges' lengths. However, this approach proved to be ineffective when the geometries have different angles between the edges, e. g. ellipsis. This was proven with the topologies tested, in such cases, the minimum value of the reconstruction error was for the double ellipsis cylinder, almost 900 % higher when computing only the lengths (error = 0.89 mm) than when including the angles (error = 0.10 mm). Although the use of angles for the reconstruction of irregular cross sections provides a better approximation than using only segments, the approach still limited and a higher number of elements will be required to provide a better approximation to the shapes. Even though the sensors' connectivity needs to be improved for a smart textile, the thickness of the sensors (1.5 mm) allows them to be attached unobtrusively into clothes and prevents them from wrinkling or creasing.

6 CONCLUSIONS

This work expands on previous work to reconstruct textile deformation from array of strain sensors by including bend sensors. We use materials and fabrication methods suitable for production process. We demonstrated that a 3.11 mm reconstruction error on complex geometries can be reduced up to 0.08 mm with the computation of angles. These innovations aim to address the challenges in sensing human body shape with practicality and ease of use. In the context of human activity recognition, such a system can be integrated in tight fitting or everyday garments to infer limbs' orientation. This could be used for gait analysis (e.g. integrated in compression leggings) or upper limb movements (e.g. integrated in shirts' sleeves. In such applications, the data would be acquired continuously (e.g. at 10 Hz), run the shape inference after each acquisition to obtain limb orientation and activity recognition techniques would be applied to the resulting time series. This could prove an attractive and unobtrusive alternative to motion sensing using wearable inertial measurement units.

REFERENCES

- [1] Manu Airaksinen, Okko Räsänen, Elina Ilén, Taru Häyrynen, Anna Kivi, Viviana Marchi, Anastasia Gallen, Sonja Blom, Anni Varhe, Nico Kaartinen, Leena Haataja, and Sampsa Vanhatalo. 2020. Automatic Posture and Movement Tracking of Infants with Wearable Movement Sensors. *Scientific Reports* 10, 1 (Jan. 2020). <https://doi.org/10.1038/s41598-019-56862-5>
- [2] Phoebe R. Apeagyei. 2010. Application of 3D body scanning technology to human measurement for clothing Fit. *International Journal of Digital Content Technology and its Applications* 4, 7 (Oct. 2010), 58–68. <https://doi.org/10.4156/jdcta.vol4.issue7.6>
- [3] Harish Devaraj, Robert Schober, Mathieu Picard, Mei Ying Teo, Cheng-Yao Lo, Wee Chen Gan, and Kean C. Aw. 2019. Highly elastic and

3D model (STL)	3D Printed model	Target geometry	Inferred shape (w/o angles)	Inferred shape (w/ angles)	Smart textile on 3D printed parts	Relative Change in Resistance
Double oval cylinder		4 rings w/11 nodes each	($\lambda_1=1, \lambda_2=0$) Error = 0.89 mm	($\lambda_1=0.65, \lambda_2=0.4$) Error = 0.10 mm	4 rings w/11 sensors each

2 cross section cone		8 rings w/11 nodes each	($\lambda_1=1, \lambda_2=0$) Error = 1.93 mm	($\lambda_1=0.8, \lambda_2=0.6$) Error = 0.11 mm	4 rings w/11 sensors each

Double oval cylinder (bent)		8 rings w/11 nodes each	($\lambda_1=1, \lambda_2=0$) Error = 2.68 mm	($\lambda_1=0.8, \lambda_2=0.9$) Error = 0.13 mm	4 rings w/11 sensors each

2 cross sections cone w/lump		8 rings w/11 nodes each	($\lambda_1=1, \lambda_2=0$) Error = 3.11 mm	($\lambda_1=0.6, \lambda_2=0.1$) Error = 0.08 mm	4 rings w/11 sensors each

Figure 5: Simulation and experimental measurements results. Column 1: STL models of the geometries. Column2: 3D printed models. Column 3: target geometry for the simulation (blue) built on the STL nodes (black). Column 4: inferred shape results without angles. Column 5: Inferred shape results with angles. Column 6: Smart textile conformed on 3D printed parts. Column 7: relative change in resistance for each sensor from rest to when on the 3D parts.

flexible multi-layered carbon black/elastomer composite based capacitive sensor arrays for soft robotics. *Measurement: Sensors* 2-4 (Aug. 2019), 100004. <https://doi.org/10.1016/j.measen.2020.100004>

- [4] Leonardo A García-García et al. 2019. Development of a Customized Wrist Orthosis for Flexion and Extension Treatment Using Reverse Engineering and 3D Printing. In *World Congress on Medical Physics and Biomedical Engineering 2018*. Springer, Springer Link.
- [5] Leonardo A. García-García, Julio C. Costa, Pasindu Lugoda, Daniel Roggen, and Niko Munzenrieder. 2020. Copper wire based electrical contacts for direct interfacing of stretchable sensors. In *2020 IEEE SENSORS*. IEEE. <https://doi.org/10.1109/sensors47125.2020.9278749>
- [6] Leonardo A García-García and Rodríguez-Salvador Marisela. 2018. Additive manufacturing knowledge incursion on orthopaedic devices : the case of hand orthoses. In *Proceedings of the 3rd International Conference on Progress in Additive Manufacturing (Pro-AM 2018)*. Nanyang Technological University, Nanyang Technological University. <https://doi.org/10.25341/D4388H>
- [7] Leonardo A. García-García and Marisela Rodríguez. 2019. Competitive and technology intelligence to reveal the most influential authors and inter-institutional collaborations on additive manufacturing for hand orthoses. *Journal of Intelligence Studies in Business* 8, 3 (Jan. 2019). <https://doi.org/10.37380/jisib.v8i3.364>
- [8] Oliver Glauser, Daniele Panozzo, Otmar Hilliges, and Olga Sorkine-Hornung. 2019. Deformation Capture via Soft and Stretchable Sensor Arrays. *ACM Transactions on Graphics* 38, 2 (April 2019), 1–16. <https://doi.org/10.1145/3311972>
- [9] N. Hasler, C. Stoll, M. Sunkel, B. Rosenhahn, and H.-P. Seidel. 2009. A Statistical Model of Human Pose and Body Shape. *Computer Graphics Forum* 28, 2 (April 2009), 337–346. <https://doi.org/10.1111/j.1467-8659.2009.01373.x>
- [10] Atis Hermanis et al. 2016. Acceleration and Magnetic Sensor Network for Shape Sensing. *Sensors Journal* (2016).

- [11] Chengyu Li, Di Liu, Chaoqun Xu, Ziming Wang, Sheng Shu, Zhuoran Sun, Wei Tang, and Zhong Lin Wang. 2021. Sensing of joint and spinal bending or stretching via a retractable and wearable badge reel. *Nature Communications* 12, 1 (May 2021). <https://doi.org/10.1038/s41467-021-23207-8>
- [12] Rongzhou Lin, Han-Joon Kim, Sippanat Achavananthadith, Selman A. Kurt, Shawn C. C. Tan, Haicheng Yao, Benjamin C. K. Tee, Jason K. W. Lee, and John S. Ho. 2020. Wireless battery-free body sensor networks using near-field-enabled clothing. *Nature Communications* 11, 1 (Jan. 2020). <https://doi.org/10.1038/s41467-020-14311-2>
- [13] F. Lorussi, E.P. Scilingo, M. Tesconi, A. Tognetti, and D. DeRossi. 2005. Strain Sensing Fabric for Hand Posture and Gesture Monitoring. *IEEE Transactions on Information Technology in Biomedicine* 9, 3 (Sept. 2005), 372–381. <https://doi.org/10.1109/titb.2005.854510>
- [14] Sitong Lu, Diansheng Chen, Che Liu, Yongkang Jiang, and Min Wang. 2019. A 3-D finger motion measurement system via soft strain sensors for hand rehabilitation. *Sensors and Actuators A: Physical* 285 (Jan. 2019), 700–711. <https://doi.org/10.1016/j.sna.2018.12.004>
- [15] Pasindu Lugoda, Júlio C. Costa, Leonardo A. Garcia-Garcia, Arash Pouryazdan, Zygimantas Jocys, Filippo Spina, Jonathan Salvage, Daniel Roggen, and Niko Münzenrieder. 2020. Coco Stretch: Strain Sensors Based on Natural Coconut Oil and Carbon Black Filled Elastomers. *Advanced Materials Technologies* 6, 2 (Dec. 2020), 2000780. <https://doi.org/10.1002/admt.202000780>
- [16] Pasindu Lugoda, Leonardo A. Garcia-Garcia, Sebastien Richoz, Niko Munzenrieder, and Daniel Roggen. 2019. ShapeSense3D. In *Proceedings of the 2019 ACM International Joint Conference on Pervasive and Ubiquitous Computing and Proceedings of the 2019 ACM International Symposium on Wearable Computers - UbiComp/ISWC '19*. ACM Press. <https://doi.org/10.1145/3341162.3343846>
- [17] Ryosuke Matsuda, Satoru Mizuguchi, Fumika Nakamura, Takuma Endo, Yutaka Isoda, Go Inamori, and Hiroki Ota. 2020. Highly stretchable sensing array for independent detection of pressure and strain exploiting structural and resistive control. *Scientific Reports* 10, 1 (July 2020). <https://doi.org/10.1038/s41598-020-69689-2>
- [18] Corinne Mattmann, Oliver Amft, Holger Harms, Gerhard Troster, and Frank Clemens. 2007. Recognizing Upper Body Postures using Textile Strain Sensors. In *2007 11th IEEE International Symposium on Wearable Computers*. IEEE. <https://doi.org/10.1109/iswc.2007.4373773>
- [19] Jun Shintake, Egor Piskarev, Seung Hee Jeong, and Dario Floreano. 2017. Ultrastretchable Strain Sensors Using Carbon Black-Filled Elastomer Composites and Comparison of Capacitive Versus Resistive Sensors. *Advanced Materials Technologies* 3, 3 (Dec. 2017), 1700284. <https://doi.org/10.1002/admt.201700284>
- [20] Nadia Thalmann. 2010. *Modeling and simulating bodies and garments*. Springer, London.
- [21] Jeroen L. A. van Vugt, Yordi van Putten, Irma M. van der Kall, Stefan Buettner, Frank C. H. D'Ancona, Helena M. Dekker, Hendrikus J. A. N. Kimenai, Ron W. F. de Bruin, Michiel C. Warlé, and Jan N. M. IJzermans. 2018. Estimated skeletal muscle mass and density values measured on computed tomography examinations in over 1000 living kidney donors. *European Journal of Clinical Nutrition* 73, 6 (Aug. 2018), 879–886. <https://doi.org/10.1038/s41430-018-0287-7>